

## Chester Metal Super SL

### DESCRIPTION:

Chester Metal Super SL is a two-element thixotropic epoxy-metallic composite **with extended working life**. The material contains modified epoxy resins, steel and fiber fillers. A steel-filled epoxy putty cures at room temperature and is designed for filling, rebuilding, and bonding metal surfaces.

### TYPICAL APPLICATION:

- STOPPING LEAKS IN PIPELINES AND TANKS.
- REPAIR OF DAMAGED SPLINEWAYS
- SEATING OF BRIDGE BEARING
- RESTORATION OF HEAT EXCHANGES
- REBUILDING OF BEARING SEATS
- CASTING DEFECTS REPAIR
- REPAIR OF CRACKS IN THE BODIES
- REBUILDING OF SHAFT NECKS
- REPAIR OF DAMAGED FLANGES

<b>Technical Data</b>				
Cured Density	----	----	<b>2,14±0,05 g/cm<sup>3</sup></b>	
Mix Ratio by Volume	----	----	<b>2 : 1</b>	
Mix Ratio by Weight	----	----	<b>3,1 : 1</b>	
Color				<b>gray</b>
Tensile Shear (Stainless Steel)	ASTM 1002	ISO 4587	<b>18,5 MPa</b>	<b>2685 psi</b>
Tensile Shear (Aluminum)	ASTM 1002	ISO 4587	<b>12,0 MPa</b>	<b>1740 psi</b>
Tensile Shear (Brass)	ASTM 1002	ISO 4587	<b>11,8 MPa</b>	<b>1710 psi</b>
Temperature Resistance Wet	----	----	<b>100°C</b>	<b>212°F</b>
Temperature Resistance Dry	----	----	<b>250°C</b>	<b>482°F</b>
Minimal working temperature	----	----	<b>-50°C</b>	<b>-58°F</b>
Heat Distortion Temperature	----	DIN 53462	<b>68°C</b>	
Ambient Cure				<b>115°C*</b>
Post Cure				<b>239°F</b>
Working Life (68°F)(20°C)	----	----	<b>65 min</b>	
Max working temperature				<b>270°C</b>
Cured Hardness	ASTM D2240	----	<b>88 °Sh D</b>	
Compressive Strength	ASTM D695	ISO 604	<b>146 MPa</b>	<b>21175 psi</b>
Thermal conductivity coefficient	----	----	<b>0.56 W/mK</b>	
Flexural strength	----	ISO 178	<b>90 MPa</b>	
Flexural modulus	----	----	<b>8560 MPa</b>	
Impact strength	----	ISO 179	<b>5,4 kJ/m<sup>2</sup></b>	

\*30 days at a temperature of 180 °C.

## Chester Metal Super SL

### DIRECTIONS FOR USE

#### Conditions during the application.

The product cannot be used at a temperature lower than 5 °C (41°F) or a relative air humidity higher than 90% and in conditions in which moisture condensation occurs on the surface to be repaired.

#### Surface preparation.

The surface of the part to be repaired should be degreased chemically or with a gas burner and mechanically cleaned - by shot blasting, sandblasting or with the use of angle grinders, pin grinding wheels, sandpaper, etc.

Always strive to thoroughly remove surface contamination and make the surface well roughened. A properly prepared surface should be degreased using e.g. Chester Fast Cleaner F-7 or Ultra Fast Degreaser F-6.

#### Mixing and application of the composition.

Use two different spatulas to take the Base and the Reactor. Mix both elements on the flat smooth surface (do not mix them in their packages) until obtaining a uniform color.

Efforts should be made to apply immediately after preparing the mixture, because the curing reaction starts immediately and any delay reduces the adhesion. Necessary layer should be placed single, carefully rubbing it into the base. In case there is necessary second layer, first shouldn't be fully cured, otherwise there should be made rough surface. In the case of repairs of cracks, it is recommended to additionally reinforce the composite with a fiberglass net.

#### Efficiency

1kg after mixing has volume 0,47 dm<sup>3</sup>.

#### Post curing

Curing at a temperature of 80-120°C(176-248°F) for minimum 2h, after initial cure considerably improves mechanical properties, heat and chemical resistance. Optimal curing process: 7 days at 20 °C and post curing for 4 hours at 120 °C.( 248°F )

### CURE TIME ACCORDING TO THE TEMPERATURE.

Ambient temperature °C (°F)	Working life [min]	Time for machining [h]
5 (41)	180	24
10 (50)	100	16
20 (68)	65	12
30 (86)	40	7

It should be remembered that the rate of the reaction significantly depends, apart from the ambient temperature, on the quantity of the used material (the bigger mass of the mixed material, the reaction rate increases). The above presented times refer to the mass of 0,25 kg of the composite.

### CHEMICAL RESISTANCE

The samples were subjected to optimal curing process. Unless otherwise stated, the tests were carried out at 20 °C (68°F).

- 1 – Prolonged immersion
- 2 – Short-term immersion
- 3 – Not recommended

Solvent	Chemical resistance
Petrol	1
Diesel fuel	1
Antifreeze	1
Motor oil	1
Petroleum	1
Nitric acid 10%	1
Nitrous acid 10%	1
Acetic acid 5%	2
Hydrochloric acid 10%	1
Ammonia 20%	1
Water 100°C(212°F)	1
Sea water	1
Ozone (dry)	1
Chlorine	1
Acetone	3
Methylene Chloride	3

Full table of chemical resistance is on the website .

### OTHER INFORMATION

#### Storage

The product should be stored in original packaging at temperature between +0°C (32 °F) to +30°C (86 °F).