

Chester Metal Super BR

DESCRIPTION:

Chester Metal Super BR is a two-element thixotropic epoxy-metallic composite. The material contains modified epoxy resins, metallic and fiber fillers. Cures at room temperature and is designed for filling, rebuilding, and bonding bronze castings.

TYPICAL APPLICATION:

- REPAIR OF DEFECTS IN BRONZE CASTINGS
- FILLING CAVITIES IN BRONZE CASTINGS

Technical Data

Cured Density	-----	-----	1,50±0,05 g/cm³	
Mix Ratio by Volume	-----	-----	2 : 1	
Mix Ratio by Weight	-----	-----	2,5 : 1	
Color			bronze	
Tensile Shear (Stainless Steel)	ASTM 1002	ISO 4587	17,0MPa	2380 psi
Tensile Shear (Mild Steel)	ASTM 1002	ISO 4587	17,0MPa	2380 psi
Tensile Shear (Aluminum)	ASTM 1002	ISO 4587	14,0 MPa	2030 psi
Temperature Resistance Wet	-----	-----	100°C	212°F
Temperature Resistance Dry	-----	-----	200°C	392°F
Minimal working temperature	-----	-----	-50°C	-58 °F
Heat Distortion Temperature	ASTM D648	ISO 75	85 °C	185°F
Working Life (68°F)(20°C)	-----	-----	20 min	
Hardness	ASTM D2240	-----	87 Sh D	
Compressive Strength	ASTM D695	ISO 604	142 MPa	20590 psi
Thermal conductivity coefficient	-----	-----	0,56 W/mK	
Flexural strength	-----	ISO 178	89 MPa	12910 psi
Impact strength	-----	ISO 179	5,6 kJ/m²	

Chester Metal Super BR

DIRECTIONS FOR USE

Conditions during the application.

The product cannot be used at a temperature lower than 5 °C (41°F) or a relative air humidity higher than 90% and in conditions in which moisture condensation occurs on the surface to be repaired.

Surface preparation.

The surface of the part to be repaired should be degreased chemically or with a gas burner and mechanically cleaned - by shot blasting, sandblasting or with the use of angle grinders, pin grinding wheels, sandpaper, etc.

Always strive to thoroughly remove surface contamination and make the surface well roughened. A properly prepared surface should be degreased using e.g. Chester Fast Cleaner F-7 or Ultra Fast Degreaser F-6.

Mixing and application of the composition.

Use two different spatulas to take the Base and the Reactor. Mix both elements on the flat smooth surface in their packages until obtaining a uniform color.

Efforts should be made to apply immediately after preparing the mixture, because the curing reaction starts immediately and any delay reduces the adhesion. Necessary layer should be placed single, carefully rubbing it into the base. In case there is necessary second layer, first shouldn't be fully cured, otherwise there should be made rough surface. In the case of repairs of cracks, it is recommended to additionally reinforce the composite with a fiberglass net.

Post curing

Post curing at a temperature of 80-110°C (176-230°F) for minimum 2h, after initial cure considerably improves mechanical properties, heat and chemical resistance.

Optimal curing process: 7 days at 20°C (68°F) and post-curing at 110°C (230°F) for 4 hours.

CURE TIME ACCORDING TO THE TEMPERATURE.

Ambient temperature °C (°F)	Working life [min]	Time for machining [h]
5 (41)	50	14
10 (50)	35	12
20 (68)	20	4

30 (86)	15	2.5
---------	----	-----

It should be remembered that the rate of the reaction significantly depends, apart from the ambient temperature, on the quantity of the used material (the bigger mass of the mixed material, the reaction rate increases). The above presented times refer to the mass of 0,25 kg of the composite.

CHEMICAL RESISTANCE

The samples were subjected to optimal curing process. Unless otherwise stated, the tests were carried out at 20 °C (68°F).

- 1 – Prolonged immersion
- 2 – Short-term immersion
- 3 – Not recommended

Solvent	Chemical resistance
Petrol	1
Diesel fuel	1
Antifreeze	1
Motor oil	1
Petroleum	1
Nitric acid 10%	1
Nitrous acid 10%	1
Acetic acid 3%	2
Amines	1
Hydrochloric acid 10%	1
Ammonia 20%	1
Water 100°C(212°F)	1
Sea water	1
Ozone (dry)	1
Chlorine	1
Acetone	3
Methylene Chloride	3

Full table of chemical resistance is on the website

OTHER INFORMATION

Storage

The product should be stored in original packaging at temperature between +0°C (32 °F) to +30°C (86 °F).